



4660 Villeneuve,
Lac-Mégantic, Québec
Canada, C6B 2C3

Tél: (819) 583-2930
Fax: (819) 583-2931

February, 17th, 1998

Surface burning characteristics : as per ASTM E84 (UL 723)

	Tafipan particleboard	Tafilam melamine
Flame spread index (FSCI) :	185.6	124.7
Smoke developed :	112.6	261.2

Those results were obtain from an independent laboratory. If you need more information, do not hesitate to contact me at 819-583-2930.

Louis Brassard
Total Quality Manager