

e COLORS / PATTERNS

TOPSTONE is available in single-tone (solo), fine-grain (duo) and coarse-grain patterns (trio) in 40 colors.



TOPSTONE PERFORMANCE DATA

PROPERTY	UNIT	RESULT	TEST METHOD	REMARK
Specific Gravity	g/cm ³	1.8		
Tensile Strength	psi	5,400	ASTM D 638	
Tensile Modulus	psi	1.4 x 10 ⁵	ASTM D 638	
Elongation	% min	0.42	ASTM D 638	
Flexural Strength	psi	9,200	ASTM D 790	
Flexural Modulus	psi	1.38 x 10 ⁵	ASTM D 790	
Hardness (Rockwell)	-	92	ASTM D 785	M scale
Thermal Expansion	mm/m, °C	3.04 x 10 ⁻⁵	ASTM D 698	
Gloss (60 degree Gardner)	-	5-26	ANSI Z136	
Color Stability	-	No change	NEMA LD3	200 hours
Wear & Cleanability	-	Passes	ANSI Z134	
Boiling Water Surface Resistance	-	No change	NEMA LD8	
High Temperature Resistance	-	No change	NEMA LD3	
Stain Resistance	-	Passes	NEMA LD3	
Impact Resistance	-	No fracture	NEMA LD3	10' ball - 36' drop - 10% ball
ICCO Impact Strength	ft. lbs/in	0.28	ASTM D2006	Notched
Water Absorption Weight	% max	0.03	ASTM D670	
Fungus and Bacteria	-	No Attack	ANSI Z134	
Weatherability	-	No change	ASTM D 1489	1000 hours